

Quality Product CertificationSeparation and Filtration

This product has been found to be fit for use in accordance with NorGeoSpec 2012 System for the function given above.

Certificate no.:	NGS-50255
Date:	20.04.2021
Valid until:	19.04.2023
Manufacturer:	Fibertex A/S
Product:	Fibertex F-27 (Produced in the plant Aalborg)
Product Type:	GTX-N
Raw material:	PP
Function:	Separation and Filtration

Issued by

Christian Recker, SINTEF Project Manager

Approved by

Arnstein Watn, Head of the Technical Committee

NorGeoSpec

NorGeoSpec

A Nordic system to call the system to call the

The products are regularly audited and tested to verify that the characteristics fulfil the NorGeoSpec 2012 Rev.: 01/14.12.2016 requirements. Approved by the NorGeoSpec Technical Committee: 13.07.2021



Certificate no.: NGS-50255

Quality Product Certification Separation and Filtration

Quality Product Certification				DoP ¹⁾	NGS			
Characteristic		Test method	Unit	DoP declared mean value	NGS declared mean value ²⁾	NGS max. tolerance ³⁾	NGS declared tolerance ⁴⁾	NGS control limits ⁵⁾
Mass per unit area		EN ISO 9864	g/m²	(-)	130	± 13.0	± 13.0	117.0-143.0
Tensile strength	MD	EN ISO 10319	kN/m	12.10	12.10	-1.21	-1.21	≥ 10.62
	CMD	EN ISO 10319	kN/m	11.50	11.50	-1.15	-1.15	
Tensile strain at tensile strength	MD	EN ISO 10319	%	42.0	42.0	-8.4	-8.0	≥ 39.0
	CMD	EN ISO 10319	%	55.0	55.0	-11.0	-11.0	
Static puncture test (CBR test)		EN ISO 12236	kN	1.800	1.800	-0.180	-0.180	≥ 1.620
Dynamic perforation test		EN ISO 13433	mm	30	30	+7.5	+7.5	≤ 37.5
Energy index		NorGeoSpec 2012	kN/m	(-)	2.1		0.0	≥ 2.1
Water permeability normal to the plane, without load		EN ISO 11058	m/s	0.070	0.070	-0.0210	-0.0210	≥ 0.0490
Characteristic opening size		EN ISO 12956	μm	80	80	± 24.0	± 24.0	56.0-104.0
Service life			years	100				

¹⁾ Manufacturer's Declaration of performance acc. hEN standards

Quality Product Certification: Separation and Filtration

Application profile: 2

²⁾ Manufacturer's declared values

Max. possible NorGeoSpec tolerance according to table 1 Part 1 and Part 2 of the guideline

Manufacturer's declared tolerance; the tolerance for the NorGeoSpec certificate shall be equal or less than the "NGS max. tolerance" (see table 1 Part 1 and Part 2 of the guideline)

NorGeoSpec control limit values regarding fitness for use; these "NGS control limits" are calculated based on the "NGS declared mean values" and the "NGS declared tolerances"; the product has to satisfy these "NGS control limits" during the NorGeoSpec certification process and random product testing